

FIXATEUR

Transparent, acrylic, solvent based primer



06.2023 V.03

Transparent, acrylic, solvent based primer suitable for exterior use. It facilitates the adhesion of the overlying emulsion, acrylic and sealant paints, it reduces the absorption of the substrate (plaster) and helps fixing difficult surfaces such as painted with adhesive or lime surfaces. It also isolates the external plaster protecting at a large scale the surface from salt appearance. Ideal primer for external walls, cement, or tarred terraces.



Stir well before use



Coverage:
5-8 m²/lt



Drying time:
Touch dry after 1-2 hours



Thinning
With white spirit at 100% by volume



Paint:
Roller



Paint:
Brush

Product Characteristics

- Very good adhesion and high penetration.
- High coverage.
- Emulsion, acrylic and sealant paint's undercoat.
- Free of ammonia, lead acetate, mercury and other heavy metals.
- Harmonized with directive 2004/42/EC.

Shades

Available in transparent.

Packaging:

1lt
5lt
15lt



The above information is based on laboratory audits and the long experience of the scientific staff of the company. The quality of the product is guaranteed by the company's operating system which is based on the requirements of ISO 9001, ISO 45001, ISO 14001 and the EMAS regulation. As producers we are not responsible for any damage or damage caused in the event that the product has not been used for the appropriate application and in accordance with its instructions for use.

BERLING SA- Paint Industry
Inofita Viotias, P.C. 32011, Greece
tel.: +30 22620 31663, fax.: +30 22620 31293
www.berling.gr / en info@berling.gr

Technical Specifications



V.O.C.	720gr/lit (max content in Volatile Organic Compounds of thinned - ready to use product).
Specific Gravity	0,84 ± 0,02gr/cm ³ (ISO 2811).
Viscosity	13 - 18 sec, 25°C (Flow cup 4 DIN 53211).
Performance	5 - 8m ² /lit, depending on the surface absorptivity.
Application	By brush or roller.
Thinning	With white spirit at 100% by volume
Drying time	Touch dry after 1 to 2 hours (the drying time might be elongated according to temperature and humidity conditions).
Recoating	It can be recoated with emulsion, acrylic, sealant, water, and relief paints after 4 to 6 hours (re-coating time might be elongated according to temperature and humidity conditions).

ACCORDING TO 2004/42/EK

PHASE II,
Subcategory h,
Binding primers,
value limit VOC =
750gr/lit, max VOC
value limit = 720gr/lit
(ready to use
product).



Storage

Storage indoors to avoid exposure to high or low surfaces and high humidity conditions. Avoid sources of heat, radiation, static electricity, and storage near food. Keep container tightly closed. After opening can use product in a short period of time. Close the can well.



Safety Instructions- Prevention of environmental harming

Minimize paint wastage by estimating how much paint you will need. Recover unused paint for reuse. Reuse of paint can effectively minimize the products life cycle environmental impact. Clean tools with water and soap. Do not put residual paint down the kitchen sink or toilet or into a waste bin. Empty cans with paint residues should be handled the same way and disposed according to local Regulations. You should ask for advice for the local government section responsible for the collection and disposal of waste. Ask for advice from an authorized body for waste recovery. Wear protective gloves and goggles/ Do not eat, drink when handling the product. Wash wand with suitable cleaning products. Keep out of reach of children. Always read the can label before use.
For further information ask for the Safety Data Sheet of the product.

The above information is based on laboratory audits and the long experience of the scientific staff of the company. The quality of the product is guaranteed by the company's operating system which is based on the requirements of ISO 9001, ISO 45001, ISO 14001 and the EMAS regulation. As producers we are not responsible for any damage or damage caused in the event that the product has not been used for the appropriate application and in accordance with its instructions for use.

BERLING SA- Paint Industry
Inofita Viotias, P.C. 32011, Greece
tel.: +30 22620 31663, fax.: +30 22620 31293
www.berling.gr /en info@berling.gr

Recommended application systems



Exterior surfaces

- New surfaces / Already painted surfaces.

Preparation

Surfaces to be painted must be dry and clean from any dirt, grease, salts or loose and flaking paint. For any existing holes, cracks or wall irregularities use Berling's Acrylic Putty or Berling's Two Component Putty prior to applying the product. The product is applied by brush or roller after being suitably thinned. Apply at temperatures between 10° C and 35° C and up to 80% in humidity.

Application Instructions

New Surfaces

For new surfaces, thin Fixateur with White Spirit at a percentage of 100% by volume and apply one coating on the surface you want to prime. Then apply two coatings of acrylic or emulsion or sealant paint, etc., following the drying and recoating time.

Old Surfaces

In case of already painted or covered by putty surfaces, surfaces that have been through chalking, peeled colors or covered with asbestos, all surfaces must be first rubbed with sandpaper. Then, apply one coating of Berling's Fixateur thinned at a proportion of 1 :1 with White Spirit and then apply two coatings of emulsion, acrylic, sealant, etc. paint following the drying and recoating times.

Terraces' Surfaces

Regarding tarred or painted terraces' surfaces, holes and wall irregularities should be filled with putty. Then, apply Fixateur thinned with White Spirit at a proportion of 50% in order to achieve not only stabilization of the old, tarred roof but also better adhesion of the sealant topcoat.

The above information is based on laboratory audits and the long experience of the scientific staff of the company. The quality of the product is guaranteed by the company's operating system which is based on the requirements of ISO 9001, ISO 45001, ISO 14001 and the EMAS regulation. As producers we are not responsible for any damage or damage caused in the event that the product has not been used for the appropriate application and in accordance with its instructions for use.