

# VELATURA

Matt undercoat for enamel paints



11.2022 V.03

High quality matt undercoat suitable for wooden and spatulated surfaces. It presents high opacity, very good adhesion and it's very easy when sanding with sandpaper. It gives a smooth and soft in touch surface, suitable for excellent finish.



**Stir well before use**



**Coverage:**  
10-13 m<sup>2</sup>/lt



**Drying time:**  
Touch dry after 1 to 2hrs



**Thinning**  
with White Spirit  
at a percentage  
up to 10% by  
volume.



**Paint:**  
Roller



**Paint:**  
Brush

## Product Characteristics

- Undercoat for wooden surfaces.
- White, matt.
- Easy to sand.
- Easy to apply.
- Very good adhesion.
- High opacity and coverage.
- Free of lead, mercury, and other heavy metals.
- Harmonized with directive 2004/42/EC.

## Shades

Available in white and bases C to create thousands of shades with Berling's tinting system.

## Packaging:

0.75lt  
2,5lt



The above information is based on laboratory audits and the long experience of the scientific staff of the company. The quality of the product is guaranteed by the company's operating system which is based on the requirements of ISO 9001, ISO 45001, ISO 14001 and the EMAS regulation. As producers we are not responsible for any damage or damage caused in the event that the product has not been used for the appropriate application and in accordance with its instructions for use.

## Technical Specifications



<b>V.O.C.</b>	350gr/lit (max content in Volatile Organic Compounds of ready to use product).
<b>Specific Gravity</b>	1,64 ± 0,02gr/cm <sup>3</sup> (ISO 2811).
<b>Viscosity</b>	110 - 120 K.U., 25°C (ASTM D562).
<b>Performance</b>	10 - 13m <sup>2</sup> /lit.
<b>Thinning</b>	Thin with White Spirit at a percentage up to 10% by volume.
<b>Application</b>	By brush or roller.
<b>Drying time</b>	Touch dry after 1 to 2 hours, through dry in 6 to 8 hours (the drying time might be elongated according to temperature and humidity conditions).
<b>Recoating</b>	Reapply after 12 hours (recoating time might be elongated according to temperature and humidity conditions).

### ACCORDING TO 2004/42/EK

PHASE II,  
Subcategory g,  
Primers, value limit  
VOC = 350gr/lit,

max VOC value  
limit = 395gr/lit  
(ready to use  
product).



### Storage

Storage indoors to avoid exposure to high or low surfaces and high humidity conditions. Avoid sources of heat, radiation, static electricity, and storage near food. Keep container tightly closed. After opening can use product in a short period of time. Close the can well.



### Safety Instructions- Prevention of environmental harming

Minimize paint wastage by estimating how much paint you will need. Recover unused paint for reuse. Reuse of paint can effectively minimize the products life cycle environmental impact. Clean tools with water and soap. Do not put residual paint down the kitchen sink or toilet or into a waste bin. Empty cans with paint residues should be handled the same way and disposed according to local Regulations. You should ask for advice for the local government section responsible for the collection and disposal of waste. Ask for advice from an authorized body for waste recovery. Wear protective gloves and goggles/ Do not eat, drink when handling the product. Wash wand with suitable cleaning products. Keep out of reach of children. Always read the can label before use.  
**For further information ask for the Safety Data Sheet of the product.**

## Recommended application systems



### New and old surfaces

- New/Old surfaces

### Application instructions

#### New Surfaces

New wooden surfaces must be sand with sandpaper and then apply one or two coatings of Berling's Velatura, sanding slightly after each coating. Then finish by applying two coatings of any enamel.

#### Old Surfaces

Clean properly already painted surfaces and remove any peeled or old paint left, using sandpaper. Apply one or two coatings of Berling's Velatura and sand with sandpaper after each coating. Finish by applying one or two coatings of the desirable topcoat, following the drying and recoating times.

The above information is based on laboratory audits and the long experience of the scientific staff of the company. The quality of the product is guaranteed by the company's operating system which is based on the requirements of ISO 9001, ISO 45001, ISO 14001 and the EMAS regulation. As producers we are not responsible for any damage or damage caused in the event that the product has not been used for the appropriate application and in accordance with its instructions for use.